

iQ TORO SC technical data

CERTIFICATION & CLASSIFICATION	STANDARDS	iQ Toro SC
Type of floor covering	ISO 10581	Permanently static conductive pressed homogeneous vinyl flooring
Binder content	ISO 10581	Type I
CE certification	EN 14041	Yes
Classification	ISO 10874	Commercial: 34 Industrial: 43

TECHNICAL CHARACTERISTICS	STANDARDS	iQ Toro SC
Wear layer thickness	ISO 24340	2.0 mm
iQ PUR		Yes
Total thickness	ISO 24346	2.0 mm
Total weight/m ²	ISO 23997	2950 g
Form of delivery	ISO 24341	Sheet (rolls)
		Approx. 23 lm x 200 cm Art. no. 3093 --- 3 digit colour number
	ISO 24342	Tiles (box)
		61 x 61 cm 14 tiles/box = 5.21 m ² Art. no. 3094 --- 3 digit colour number


TECHNICAL PERFORMANCES	STANDARDS	iQ Toro SC
Dimensional stability	ISO 23999	≤ 0.40% for rolls ≤ 0.25% for tiles
Reaction to fire	EN ISO 13501-1 EN ISO 9239-1 EN ISO 11925-2	Class B _{fl} s1 ≥ 8 kW/m ² Pass
Residual indentation	ISO 24343-1	Required value: ≤ 0.10mm Best measured value: 0.02 mm
Castors chair test	ISO 4918	Suitable
Static electrical discharge	EN 1815	< 2 kV
Electrical insulation	VDE 0100, Part 600	R _i ≤ 5 x 10 ⁴ Ohms
Electrical resistance	ESD-approval SP-method 2472 EN 1081	R ≤ 10 ⁹ Ohms R ₁ 5x10 ⁴ ≤ R ≤ 10 ⁶ Ohms R ₂ 5x10 ⁴ ≤ R ≤ 10 ⁶ Ohms R 5x10 ⁴ ≤ R ≤ 10 ⁶ Ohms ≤ 3.5x10 ⁷ Ohms
Clean room test	EN/IEC 61340-4-1 / 100 V EN/IEC 61340-4-5	Class A
Clean room test	ASTM F24 F51	Class A
Ease of decontamination	ISO 8690	Good
Total VOC emissions	AgBB/DIBt	≤ 10 µg/m ³ (after 28 days)
Underfloor heating		Suitable - max. 27°C
Thermal resistance	EN 12667	Approx. 0.01 m ² K/W
Light fastness	EN ISO 105-B02	≥ level 7
Chemical resistance	ISO 26987	Good resistance
Bacteria resistance	ISO 846:Part C	Does not favour growth
Slip resistance	DIN 51130 EN 13896	R9 ≥ 0.3
Seam strength	EN 684	Average value: ≥ 240 N/50 mm Individual values: ≥ 180 N/50 mm
Colours		14

The above information is subject to modification for the benefit of further improvement. (05/16).


CUSTOMS TARIFF: 482050000000F

Tarkett's instructions regarding installation, cleaning and maintenance should be observed. Please contact Tarkett at the address shown for these instructions.

iQ Toro SC	NCS N°	Welding Rod No.	iQ Toro SC	NCS N°	Welding Rod No.	iQ Toro SC	NCS N°	Welding Rod No.	iQ Toro SC	NCS N°	Welding Rod No.
100	S 1002-Y50R	1287 322	104	S 1005-Y40R	1288 255	572	S 1515-Y30R	1287 438	576	S 4020-G50Y	1287 309
101	S 2502-B	1291 811	105	S 2020-Y30R	1292 372	573	S 2030-Y30R	1287 059	578	S 6502-B	1291 216
102	S 4502-B	1292 383	107	S 2020-R90B	1291 210	574	S 4005-Y50R	1287 379			
103	S 8502-B	1292 384	570	S 1502-Y50R	1287 531	575	S 7005-Y80R	1287 456			



Logistics Information



General Information



According to European Classification ISO 10874 - EN 685



WESTERN EUROPE: Austria: Tarkett Holding GmbH, Niederlassung Wien - Tel. +43 1 47 88 062 ■ Belgium: Tarkett France Belux - Tel. +32 16 35 98 80 ■ Denmark: Tarkett A/S - Tel. +45 43 90 60 11 ■ Finland: Tarkett Oy - Tel. +358 9 4257 9000 ■ France: Tarkett SAS - Tel. +33 1 41 20 42 49 ■ Germany: Tarkett Holding GmbH, Bereich Objekt - Tel. +49 62 33 810 ■ Greece: Tarkett Monoprosopi Ltd - Tel. +30 210 6745 340 ■ Italy: Tarkett S.p.A. - Tel. +39 0744 7551 ■ Luxembourg: Tarkett GDL SA - Tel. +352 949 211 8804 ■ Netherlands: Tarkett Holding GmbH, Vestiging Nederland - Tel. +31 416 685 491 ■ Norway: Tarkett AS - Tel. +47 32 20 92 00 ■ Portugal: Tarkett SA - Tel. +351 21 427 64 20 ■ Spain: Tarkett Floors S.L. - Tel. +34 91 358 00 35 ■ Sweden: Tarkett Sverige AB - Tel. +46 771 25 19 00 ■ Switzerland: Tarkett Holding GmbH, Bereich Objekt Schweiz - Tel. +41 043 233 79 24 ■ Turkey: Tarkett Aspen - Tel. +90 212 213 65 80 ■ United Kingdom: Tarkett Ltd - Tel. +44 (0) 1622 854 040 ■ **EASTERN EUROPE:** Baltic Countries: Tarkett Baltics - Tel. +370 37 262 220 ■ Czech Republic: Tarkett France SAS, org. slozka - Tel. +420 271 001 602 ■ Hungary: Tarkett France SAS - Tel. +36 1 437 8150 ■ Poland: Tarkett Polska Sp. z o.o. - Tel. +48 22 16 09 231 ■ Russian Federation: ZAO Tarkett RUS - Tel. +7 495 775 3737 ■ Slovakia: Tarkett France SAS, org. zlozka - Tel. +421 248 291 317 ■ South East Europe: Tarkett Trade d.o.o. - Tel. +381 21 7557 649 (44) 569 12 21 ■ Ukraine: Tarkett UA - Tel. +38 (0) 44 569 12 21 ■ **ASIA AND OCEANIA:** Australia: Tarkett Australia Pty Ltd - Tel. +61 2 88 53 12 00 ■ China: Tarkett Floor Covering (Shanghai) Co. Ltd. - Tel. +86 (21) 60 95 68 38 ext 841 ■ North East Asia: Tarkett Hong Kong Limited - Tel. +852 2511 8716 ■ India: Tarkett France (India Branch) - Tel. +91 11 4352 4073 ■ South East Asia: Tarkett Flooring Singapore Pte. Ltd. - Tel. +65 6346 1585 ■ **AFRICA:** Tarkett International - Tel. +33 1 41 20 41 01 ■ **MIDDLE EAST:** Tarkett Middle East - Tel. +961 1 51 3363/4 ■ Israel: Tarkett International - Tel. +33 1 41 20 41 01 ■ **NORTH AMERICA:** USA: Tarkett Inc. - Tel. +1 713 869 5811 / Johnsonite - Tel. +1 440 543 8916 ■ Canada: Tarkett Inc. - Tel. +1 450 293 173 ■ **LATIN AMERICA:** Brazil: Tarkett - Tel. 55 12 3954 7108 ■ Argentina - Chile - Uruguay: Tarkett Latam Mercosur - Tel. +54 11 47 08 0772 / +54 9 11 44 46 88 82 ■ Bolivia - Colombia - Ecuador - Panama - Paraguay - Peru - Trinidad and Tobago - Venezuela: Tarkett - Tel. +55 11 9 8410 9310 / +55 11 95494 0069 ■ Mexico / Central America: Tarkett Latam Mexico - Tel. +55 11 98410 9310